




**PALCLAD™**  
Hygienic Wall Cladding System  
**Colour Palette**



# PALCLAD™ Colour Palette

## PALCLAD™ Prime



Jade | LRV 33




Granite | LRV 6




Peacock | LRV 10



Dolphin grey | LRV 29



Enchanted | LRV 34



Bluebird | LRV 8



Siren | LRV 3



Candy floss | LRV 13




Sugar Plum | LRV 1




Black Ice | LRV 0

## White



Palclad Porcelain White | LRV 83




Gloss White\* | LRV 87




Palclad™ M660\* | LRV 77

## Pastels




Blue | LRV 52



Grey | LRV 54



Cream | LRV 66



Mint | LRV 70

[ LRV = Light Reflective Value. ]

\* Tin stabilised formulation

# PALCLAD™ Prime - Hygienic Wall Cladding System

Complete cladding system

## Main Benefits



14 Designer colours



Smooth satin finish with low glare/reflective surface.  
Optional Gloss white.



No toxic ingredients  
Calcium Zinc formulation (CaZn)  
RohS and REACH Compliant



High impact  
resistance



Excellent chemical  
resistance



Excellent fire resistance  
With an optional  
Low Smoke (s2) grade

- Creates a high sanitation environment.
- Withstands repeated cleaning cycles.
- Versatile design options facilitated through multiple colours and accessories.
- Full hygienic cladding system including colour matched profiles, weld rods, sealants and adhesives.
- Made in the UK.
- CE marked for cladding applications.

## Dimensions

Thickness	Width x Length
2.5 mm	1220 x 3050 mm
2.5 mm	1220 x 2440 mm

Custom Thicknesses and sizes are available upon request, subject to MOQ and production lead times.  
Maximum sheet width up to 1500mm available upon request.

## Panel Physical Properties

Property	Method*	Conditions	Units	Value
Density	ASTM D792		g/cm <sup>3</sup>	1.4
Heat Deflection Temperature (H.D.T)	ASTM D648	Load: 1.82 MPa	°C	60
Service Temperature			°C	0 to 50
Coefficient of Linear Thermal Expansion	DIN 53752	20°C - 90°C	10 <sup>-5</sup> /k	6.7
Thermal Conductivity	ASTM C177		W/mK	0.15
Tensile Strength at Yield	ASTM D-638	10 mm/min	MPa	45
Elongation at Break	ASTM D-638	10 mm/min	%	>80
Modulus of Elasticity	D-638	1 mm/min	MPa	2,900
Flexural strength	D-790	1.3 mm/min	MPa	80
Flexural modulus	D-790	1.3 mm/min	MPa	2,700
Water Absorption	ISO 62	216 h		≤0.1%
Water Vapour Transmission	ASTM E96		g/m <sup>2</sup> /24hr	≤0.12
Impact Strength	ASTM D256	Notched Izod	kJ/m <sup>2</sup>	>8
Surface Resistivity	ASTM D257		Ω	>10 <sup>14</sup>

\* ASTM except where noted otherwise

## Flammability

Standard	Classification	Standard	Classification
EN 13501	B, s3, d0	BS476 Part 6/7	Class 0, Class 1



CONSTRUCTION

\* All the above depends on thickness and colours.  
For additional information please contact PALRAM.



**PALRAM EUROPE LTD.**  
Tel: +44.1302.380738  
Fax: +44.1302.380788  
[Cladding.uk@palram.com](mailto:Cladding.uk@palram.com)  
[www.palram.com](http://www.palram.com)



8826598 - 08.2019

In as much as Palram Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Palram Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. Palram Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local Palram Industries supplier to ensure that you have obtained the most up to date information.

